



PRODUCTION INSTRUCTION OF PO - 1860 / AO-AOA-2 / 15671 STONE

DESCRIPTION	50*80
Party Quality	1700
Party Weight	0.68
Production Quality	1848
Production Weight	0.74
Pile Height - A	0
Pile Height - B	0
Pile Height - C	0
Stitching 10 Cm A	0
Stitching 10 Cm B	0
Stitching 10 Cm C	0
Width in Line 5 cms	0
Niddle Gape / Weaving Com	CAM GAPE
1. Yarn UV/Non UV	UVC
2. Canvas UV/Non UV	CANVAS 64 .600 GSM N
3. Canvas Size	64
4. Canvas Quality	.600
5. Canvas Weight @ PC.	0
6. Canvas Cutting Size	0
7. Pipen Tanki Fold	AS PER SAMPLE
8. Stiching in 5 CMS	8-9
9. Pipen Folder MM	AS PER SAMPLE
10. Latex	NO
11. Export Packing	YES

12. Carving	NO
TUMBLER / WASHING	0
PC DYEING WEIGHT	.730
PC WASHING WEIGHT	0
TUMBLING WEIGHT	0
TUFFTING FINAL WEIGHT	.720-.740
EXTRA WORK WEIGHT	0
ORDER QUANTITY	960