



PRODUCTION INSTRUCTION OF PO - 1908 / AO-AOG-3 / FELIX(BORDER) 53016

DESCRIPTION	50*80	55*105	65*130
Party Quality	1700	1700	1700
Party Weight	0.68	.980	1.435
Production Quality	1723	1723	1723
Production Weight	0.69	.990	1.445
Pile Height - A	11-12 MM	11-12 MM	11-12 MM
Pile Height - B	30-31 MM	30-31 MM	30-31 MM
Pile Height - C	0	0	0
Stitching 10 Cm A	26-27	26-27	26-27
Stitching 10 Cm B	19-20	19-20	19-20
Stitching 10 Cm C	0	0	0
Width in Line 5 cms	11 LINE	11 LINE	11 LINE
Middle Gape / Weaving Com	CAM GAPE	CAM GAPE	CAM GAPE
1. Yarn UV/Non UV	UVC	UVC	UVC
2. Canvas UV/Non UV	CANVAS 64 .600 GSM	CANVAS 64 .600 GSM	CANVAS 64 .600 GSM
3. Canvas Size	64	46	54
4. Canvas Quality	.600	.600	.600
5. Canvas Weight @ PC.	.260	.390	.575
6. Canvas Cutting Size	51*84	57*116	67.137
7. Pipen Tanki Fold	AS PER SAMPLE	AS PER SAMPLE	AS PER SAMPLE
8. Stiching in 5 CMS	8-9	8-9	8-9
9. Pipen Folder MM	42 MM	42 MM	42 MM
10. Latex	YES	YES	YES
11. Export Packing	YES	YES	YES

12. Carving	NO	NO	NO
TUMBLER / WASHING	0	0	0
PC DYEING WEIGHT	0	0	0
PC WASHING WEIGHT	0	0	0
TUMBLING WEIGHT	.680	.980	1.435
TUFFTING FINAL WEIGHT	.670-.690	.970-.990	1.425-1.445
EXTRA WORK WEIGHT	0	0	0.670-.690
ORDER QUANTITY	1080	720	360